



AMENDMENTS TO THE CLAIMS

1. **(Currently amended)** A resin for a photoresist composition, having a first structural unit that comprises a hydroxyl group bonded to a carbon atom at a polymer terminal, wherein ~~[[a]] carbon atom in an α position to said hydroxyl group has at least one electron attractive group~~ the first structural unit comprises a $-\text{CR}^1\text{R}^2\text{OH}$ group, wherein R^1 and R^2 each represent, independently, an alkyl group, halogen atom, or halogenated alkyl group, and at least one of R^1 and R^2 is an electron attractive group selected from the group consisting of halogen atoms and halogenated alkyl groups, wherein said $-\text{CR}^1\text{R}^2\text{OH}$ group is located at a polymer terminal of said resin.
2. **(Canceled).**
3. **(Original)** A resin for a photoresist composition according to claim 1, wherein said electron attractive group is a fluorine atom or a fluorinated alkyl group.
4. **(Currently amended)** A resin for a photoresist composition according to claim 1 [[2]], wherein a proportion of the first structural units (M1) unit comprising said $-\text{CR}^1\text{R}^2\text{OH}$ group is at least 1 mol%, relative to a combined 100 mol% of all structural units other than said first structural units (M1) unit within said resin for a photoresist composition.
5. **(Currently amended)** A resin for a photoresist composition ~~having~~ according to claim 1, wherein said first structural comprises a substituent with a pKa value within a range from 6 to 12 at a polymer terminal.
6. **(Canceled)**
7. **(Previously presented)** A resin for a photoresist composition according to claim 1, further comprising an acid dissociable, dissolution inhibiting group.

8. **(Original)** A resin for a photoresist composition according to claim 7, further comprising (a1) a structural unit derived from a (meth)acrylate ester having an acid dissociable, dissolution inhibiting group, and (a2) a structural unit derived from a (meth)acrylate ester having a lactone ring.
9. **(Original)** A resin for a photoresist composition according to claim 8, further comprising (a3) a structural unit derived from a (meth)acrylate ester having a hydroxyl group.
10. **(Previously presented)** A resin for a photoresist composition according to claim 1, with a weight average molecular weight of no more than 12,000.
11. **(Previously presented)** A photoresist composition, comprising a resin for a photoresist composition according to claim 1.
12. **(Original)** A photoresist composition according to claim 11, further comprising an acid generator as a component (B).
13. **(Original)** A photoresist composition according to claim 12, comprising as said component (B), (b-0) an onium salt that comprises a fluorinated alkylsulfonate ion as an anion.
14. **(Original)** A photoresist composition according to claim 12, comprising as said component (B), a sulfonium compound represented by either of general formulas (b-1) and (b-2) shown below:



wherein, X represents an alkylene group of 2 to 6 carbon atoms in which at least one hydrogen atom has been substituted with a fluorine atom; Y and Z each represent, independently, an alkyl group of 1 to 10 carbon atoms in which at least one hydrogen atom has been substituted with a fluorine atom; R^1 to R^3 each represent, independently, an aryl group or an alkyl group, and at least one of R^1 to R^3 is an aryl group.

15. **(Original)** A photoresist composition according to claim 14, further comprising as said component (B), (b-0) an onium salt that comprises a fluorinated alkylsulfonate ion as an anion.

16. **(Original)** A photoresist composition according to claim 11, further comprising a nitrogen-containing organic compound.

17. **(Original)** A method for forming a resist pattern, using a photoresist composition according to claim 11.

18. **(New)** A resin for a photoresist composition according to claim 1, wherein a proportion of the first structural units constituting said resin is 1-5 mol%, relative to a combined 100 mol% of all structural units other than said first structural units within said resin.

19. **(New)** A resin for a photoresist composition according to claim 1, wherein the first structural unit which includes the carbon atom in the α -position of said hydroxyl group having at least one electron attractive group is substantively bonded only to the polymer terminal.

20. **(New)** A resin for a photoresist composition according to claim 5, wherein a proportion of the first structural units which have the substituents with a pKa value between 6 and 12 constituting said resin is 1-5 mol% relative to a combined 100 mol% of all structural units other than said first structural units within said resin.

21. **(New)** A resin for a photoresist composition according to claim 5, wherein the substituents with a pKa value between 6 and 12 are substantively bonded only to the polymer terminal.